## WHAT IS CLAIMED IS:

- A light diffuser comprising a thermoplastic layer containing thermoplastic polymeric material and microvoids having a substantially circular cross-section in a plane perpendicular to the direction of light travel and having a diffuse light transmission efficiency of at least 65%.
- 2. The light diffuser of Claim 1 wherein the difference in refractive index between the thermoplastic polymeric material and the microvoids is greater than 0.2
- The light diffuser of Claim 1 wherein said microvoids are formed by organic microspheres.
- The light diffuser of Claim 1 wherein said microvoids are substantially free of scattering inorganic particles.
- ${\it 5.} \ The \ light \ diffuser \ of \ Claim \ 1 \ wherein \ the \ microvoids \ contain \ cross-linked \ polymer \ beads.$
- 6. The light diffuser of Claim 1 wherein the microvoids contain a gas.
- 7. The diffuser of Claim 1 where thickness uniformity across the light diffuser is less than 0.10 micrometers.
- 8. The light diffuser of Claim 1 wherein the elastic modulus of the light diffuser is greater than 500 MPa .
- 9. The light diffuser of Claim 1 wherein the impact resistance of the light diffuser is greater than 0.6 GPa.

- The light diffuser of Claim 1 wherein said light transmission is greater than 80%.
- 11. The light diffuser of Claim 1 wherein said light transmission is greater than 87%.
- 12. The light diffuser of Claim 1 wherein said microvoids have a major axis diameter to minor axis diameter ratio of less than 2.0.
- 13. The light diffuser of Claim 1 wherein said microvoids have a major axis diameter to minor axis diameter ratio of between 1.6 and 1.0.
- 14. The light diffuser of Claim 1 wherein said thermoplastic layer contains greater than 4 index of refraction changes greater than 0.20 parallel to the direction of light travel.
- 15. The light diffuser of Claim 1 wherein said microvoids have a average volume of between 8 and 42 cubic micrometers over an area of 1 cm<sup>2</sup>.
- 16. The light diffuser of Claim 1 wherein said microvoids have a average volume of between 12 and 18 cubic micrometers over an area of 1 cm $^2$ .
- 17. The light diffuser of Claim 1 wherein the said light diffuser has a thickness less than 250 micrometers.
- 18. The light diffuser of Claim 1 wherein the said light diffuser has a thickness between 12.5 and 50 micrometers.
- The light diffuser of Claim 1 wherein said thermoplastic layer comprises polyolefin polymer.

- The light diffuser of Claim 1 wherein said thermoplastic layer comprises polyester polymer.
- 21. The light diffuser of Claim 5 wherein said cross linked polymer beads have a mean particle size less than 2.0 micrometers.
- 22. The light diffuser of Claim 5 wherein said cross linked polymer beads have a mean particle size between 0.30 and 1.7 micrometers.
- 23. A back lighted imaging media comprising a light source and a thermoplastic layer containing a thermoplastic polymer material and microvoids having a substantially circular cross-section in a plane perpendicular to the direction of light travel and having a diffuse light transmission efficiency of at least 65%.
- 24. An liquid crystal device comprising a light source and a thermoplastic layer containing microvoids having a substantially circular crosssection in a plane perpendicular to the direction of light travel and having a diffuse light transmission efficiency of at least 65% wherein said thermoplastic layer is located between the light source and a polarizing film.
- 25. A liquid crystal device component comprising a light source and a thermoplastic layer containing microvoids having a substantially circular cross-section in a plane perpendicular to the direction of light travel and having a diffuse light transmission efficiency of at least 65%.